

thermally conductive / 2 part / dispensable / Form-in-Place

TAD-N-PU-2C is a thermally conductive two part thixotropic PU-adhesive with thermally conductive fillers in both components. It cures once the two parts come into contact without requiring heat or primer. It has good wetting and high bonding adhesion to most surfaces. The system cures at room temperature or by accelerated heat.

Because of its thixotropic properties, the material can also be used as dispensable 2 part form-in-place gap filler that cures precisely positioned in place. This allows for compensating extreme tolerances and spaces at non-coplanar systems.



Release 04 / 2024

PROPERTIES

- Thermal conductivity: 2 W/mK
- Very high bonding properties
- Extraordinary chemical resistance and longterm stability
- Zero stress on components
- Heat accelerated curing

AVAILABILITY

- 400 ml (2 x 200 ml) twin cartridges
- 2 x 1 kg cans
- 18 l in pails

APPLICATION EXAMPLES

- LED systems
- Processor cooling
- Memory chip assembly
- CPU boards
- EHV battery systems

Technical Data Sheet

PROPERTY	UNIT	A-Part	B-Part
MATERIAL		Polyurethane	Polyurethane
Colour		Black	White
Viscosity @ 5 rpm / 10 rpm	Pas	300 / 284	272 / 165
Viscosity (Mixed) @ 5 rpm	Pas		520
Specific Gravity	g/cm ³	2.3	2.6
Specific Gravity (Mixed)	g/cm ³		2.45
Hardness	Shore D		70
Mixing Ratio	Volume		1 : 1
Tensile Shear Strength (AI)	psi		1,380
Tensile Strength	psi		2,030
Elongation	%		30
Shelf Live @ 25 °C	Months		6
Curing Time @ 25 °C			< 24 h
Flammability	UL 94		V0
RoHS Conformity	2015 / 863 / EU		Yes
THERMAL			
Thermal Conductivity ¹	W/mK		2.0
Operating Temperature Range	°C		- 40 to + 85
ELECTRICAL			
Dielectric Strength	kV/mm		13.5
Volume Resistivity	Ohm - cm		4.55 x 10 ¹²

Measurement technique according to: ¹ASTM D 5470. All data without warranty and subject to change. Please contact us for further data and information.

All technical data and information are without warranty and believed to be reliable and accurate, corresponding to the latest state of the art. Since the products are not provided to conform with mutually agreed specifications and their use and processing are unknown we cannot guarantee results, freedom from patent infringement, or their suitability for any application. Product testing by the applicant is recommended. We reserve the right of changes.